

iD Click Ultimate 55-70 & 55-70^{PLUS}

TECHNICAL DATA

CLASSIFICATION	Standards	iD Click Ultimate 70	iD Click Ultimate 55	iD Click Ultimate 70 ^{PLUS}	iD Click Ultimate 55 ^{PLUS}
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	23 - 34 - 43*	23 - 33 - 42*	23 - 34	23 - 33
TECHNICAL CHARACTERISTICS					
Total thickness	EN ISO 24346	6,50 mm	6,50 mm	6,50 mm	6,50 mm
Wear layer thickness	EN ISO 24340	0,70 mm	0,55 mm	0,70 mm	0,55 mm
Total weight	EN ISO 23997	11,30 kg/m ²	11,40 kg/m ²	11,30 kg/m ²	11,40 kg/m ²
Wear layer binder content	EN ISO 10582	Type I	Type I	Type I	Type I
Dimensions	EN ISO 24342 Planks - - - - - EN ISO 24342 Tiles	-	-	176 x 1213 cm, 6 planks/box = 1,28 m ²	176 x 1213 cm, 6 planks/box = 1,28 m ²
		20.05 x 120.00 cm, 5 planks/box= 1,20 m ²	20.05 x 20.00 cm, 5 planks/box= 1,20 m ²	-	-
		24.30x150.00 cm, 3 planks/box = 1,09 m ²	24.30 x 150.00 cm, 3 planks/box = 1,09 m ²	-	-
		48.00 x 96.00 cm, 3 tiles/box = 1,38 m ²	48.00 x 96.00 cm, 3 tiles/box = 1,38 m ²	-	-
		48.00 x 48.00 cm, 5 tiles/box = 1,15 m ²	48.00 x 48.00 cm, 5 tiles/box = 1,15 m ²	-	-
24.30 x 48.60 cm, 11 tiles/box = 1,30 m ²	24.30 x 48.60 cm, 11 tiles/box = 1,30 m ²	-	-		
Surface treatment (PUR)		Yes - PUR Ultimate	Yes - PUR Ultimate	Yes - PUR Ultimate	Yes - PUR Ultimate
Beveled edges		Yes	Yes	Yes	Yes
Embossing in Register		No	No	Yes on PLUS references	Yes on PLUS references
TECHNICAL PERFORMANCES					
Dimensional stability	EN ISO 23999	Average measured value: 0.05% Required value: ≤ 0.15%	Average measured value: 0.05% Required value: ≤ 0.15%	Average measured value: 0.05% Required value: ≤ 0.15%	Average measured value: 0.05% Required value: ≤ 0.15%
Curl resultant to heat	EN ISO 23999	≤ 1 mm	≤ 1 mm	≤ 1 mm	≤ 1 mm
Reaction to fire	EN 13501-1	B _{fl} -s1	B _{fl} -s1	B _{fl} -s1	B _{fl} -s1
Residual indentation	EN ISO 24343-1	Average measured value: 0,02 mm Required value: ≤ 0,10 mm	Average measured value: 0,02 mm Required value: ≤ 0,10 mm	Average measured value: 0,02 mm Required value: ≤ 0,10 mm	Average measured value: 0,02 mm Required value: ≤ 0,10 mm
Furniture leg	EN 424	No damage	No damage	No damage	No damage
Castor chair	ISO 4918 - EN 425	No damage	No damage	No damage	No damage
Impact sound reduction	NF EN ISO 717 / 2	ΔL _w 19 dB / ΔL _{lin} 7 dB	ΔL _w 19 dB / ΔL _{lin} 7 dB	ΔL _w 19 dB / ΔL _{lin} 7 dB	ΔL _w 19 dB / ΔL _{lin} 7 dB
Reduction of in-room impact noise	NF S31-074	Class C (L _{new} < 85 dB)	Class C (L _{new} < 85 dB)	Class C (L _{new} < 85 dB)	Class C (L _{new} < 85 dB)
Thermal resistance	EN ISO 10456	0,05 m ² K/W	0,05 m ² K/W	0,05 m ² K/W	0,05 m ² K/W
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6	≥ 6	≥ 6	≥ 6
Chemical resistance	EN ISO 26987	Very Good	Very Good	Very Good	Very Good
Slip resistance	DIN 51130 EN 13893	R9 μ ≥ 0,30	R9 μ ≥ 0,30	R9/R10 Depending on embossing μ ≥ 0,30	R9/R10 Depending on embossing μ ≥ 0,30
Peeling resistance	EN ISO 24345	≥ 50N / 50mm	≥ 50N / 50mm	≥ 50N / 50mm	≥ 50N / 50mm
Underfloor heating		Suitable - max. 27 °C	Suitable - max. 27 °C	Suitable - max. 27 °C	Suitable - max. 27 °C
ENVIRONMENTAL PERFORMANCES					
TVOC 28 days	ISO 16000-9	≤ 10μg/m ³	≤ 10μg/m ³	≤ 100μg/m ³	≤ 100μg/m ³
Recyclable		100%	100%	100%	100%
Plasticizer		Phthalate-free	Phthalate-free	Phthalate-free	Phthalate-free
WARRANTIES					
Commercial warranty		10 years	10 years	10 years	10 years
CE MARKING					
DoP number		0197-0052-DOP-2019-03	0197-0053-DOP-2019-03	0132-0070-DoP-2018-01	0132-0070-DoP-2018-01

*References available with industrial classification 42/43 are designed without acoustic backing. The above information is subject to modification for the benefit of further improvement. (07/19).

According to the European Regulation N° 305/2011 for CE Marking, the Declarations of Performance are available on our website www.tarkett.com

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.



Produced under license from I4F
<http://www.i4f-patents.com>



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

CUSTOMS TARIFF: 4820 5000 00

